



Prüfbericht - Nr.: 238114068a1 001		Seite 1 von 2	
<i>Test Report No.:</i>		<i>Page 1 of 2</i>	
Auftraggeber:	TAITA CHEMICAL COMPANY LIMITED KAOHSIUNG BRANCH		
<i>Client:</i>	No. 5, Industrial 1st Road, Lin Yuan District , Kaohsiung, Taiwan, R.O.C.		
Gegenstand der Prüfung:	發泡級聚苯乙烯 EXPANDABLE POLYSTYRENE		
<i>Test Item:</i>			
Bezeichnung:	301MM/T/SB/SN/S/SS/F/H; 351MM/T/SB/S/SS/F/H;		
<i>Identification:</i>	351MMA/TA/SBA/SA/SSA /FA/HA; 351TAA/SBAA/SAA/SSAA/FAA; 351SK; 361MM/T/SB/S/SS/F/H; 391MM/T/SB/S/SS/F/H; 301VMM/VT/VSB/VS/VSS/VF/VH; 331X		
Anlieferungszustand:	apparent good	Eingangsdatum:	2019-12-30
<i>Delivery condition:</i>		<i>Date of Receipt:</i>	
Prüfort:	TÜV Rheinland Hong Kong Ltd.		
<i>Testing location:</i>			
Prüfgrundlage:	Testing according to customers specification for the following parameters:		
<i>Test specification:</i>	FDA 21 CFR 177.1640 - Residue of Styrene Monomer		
Prüfergebnis:	The test results are the measurements, stated in the test report.		
<i>Test result:</i>			
geprüft: tested by:	kontrolliert: checked by:		
			
2020-01-15	Yueh-Li Lin /Senior Project Coordinator	2020-01-15	Arthur Cheng /Project Manager
Datum	Name/Stellung	Unterschrift	Datum
<i>Date</i>	<i>Name/Position</i>	<i>Signature</i>	<i>Date</i>
Sonstiges/ Other Aspects:	<p>Test period: 2019-12-30 – 2020-01-15 Other company name provided by client: TAITA CHEMICAL COMPANY LIMITED; 12F., No. 39, Jihu Road, Neihu Dist., Taipei, Taiwan, R.O.C. Test sample is model "301MM" All the above models are same material as client's declaration dated on 2019-12-31.</p>		
Abkürzungen:	ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar	Abbreviations:	ok / P = passed fail / F = failed n.a. / N = not applicable
<p>Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.</p> <p><i>This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.</i></p>			

Test Report No. : 238114068a1 001
 Customer : TAITA CHEMICAL COMPANY LIMITED KAOHSIUNG BRANCH

2020-01-15

1. Residue of Styrene Monomer in Polystyrene and rubber-modified polystyrene

Test method: With reference to FDA 21 CFR 177.1640(d)

Limit: FDA 21 CFR 177.1640(c)

Sample	發泡級聚苯乙烯 EXPANDABLE POLYSTYRENE		
Material	plastic/whitie		
Lab.-No.	TCL191230-04		
Parameter	Unit	Result	Limit
Residual styrene monomer	%	0.058	0.5 / 1

Abbreviations:

% = Percentage
 < = Less than

Remark:

*1 According to FDA 21 CFR 177.1640 (c), articles in contact with food should not exceed the following limits:

Category*	Unit	Description	Total Residual Styrene Monomer
1.	%	Polystyrene basic polymers produced by the polymerization of styrene	1
2.	%	Polystyrene basic polymers when used in contact with fatty foods	0.5
3.	%	Rubber-modified polystyrene basic polymers produced by combining styrene-butadiene copolymers and/or polybutadiene with polystyrene	0.5

*2 The examined item does meet the requirement

Test Sample



--- End of Test-Report ---